Diverse ASTM Test Method-A Rugotests vergelijkingsplaten
Elco 125, 129 and 130 Surface Comparators



Rugotest no.: 1



Elco no.:130 (is inclusief meetplaatjes **Rugotest 1**)

The **Elco 130** Rugotest Surface Comparator (**Including comparator RUGOTEST 1**) includes the **grinded,turned,lapped and milled versions** on the same block, labelled **N2,N4,N5,N6, N7, N8, N9, N10** and (equivalent to: 0.05, 0.1, 0.2, 0.4, 0,8, 1.6, 3.2, 6.3, and 12.5 **Ra.roughness averages respectively).**

The **Elco 125** conforms to ISO 8503 Parts 1 and 2. Grit: 25, 60, 100 and 150µm sections. **Shot:** 25, 40, 70 and 100µm sections.

The **Elco 129** Rugotest Surface Comparator (**RUGOTEST 3**) includes the **shot and grit** blastedversions on the same block, labelled **N6, N7, N8, N9, N10 and N11** (equivalent to 0.8, 1.6, 3.2 6.3, 12.5 and 25µm roughness averages respectively).
The roughness is also shown in classes and groups